



Technical Data Sheet

Iron Sentry™ 121 – Spray Polyurethane Sealer MCP1334A and MCP1334B

Product Information

Iron Sentry™ Spray Sealer is an exterior grade, two component, reactive cure, polyurethane sealer. It is designed for use as a surface coating where durability, high abrasion resistance, flexibility and low life cycle costs are required. When properly applied, it has outstanding adhesion to metal, urethane foam, EPDM rubber and most other conventional roofing surfaces. Iron Sentry™ Sealer resists the effects of mold, mildew, fungus and other parasites.

Typical Properties

Property	Value
Finished Appearance	Flexible Red Rubber-like Membrane
Specific Gravity (MCP1334A) liquid component	1.17 to 1.23
Specific Gravity (MCP1334B) liquid component	1.07 to 1.13
Viscosity at 70° F (MCP1334A) liquid component	2800 cps to 3800 cps
Viscosity at 70° F (MCP1334B) liquid component	3600 cps to 4600 cps
Mixing Ratio MCP1334A to MCP1334B	One to one by volume
Tensile Strength (ASTM D-412) membrane	1000 psi to 1300 psi
Elongation (ASTM D-412) membrane	140% to 170%
Hardness (ASTM C-518) membrane	60 Shore A to 70 Shore A
Water Vapor Permeability (ASTM D-96) 48 mil membrane	Less than 0.002 perms
Coverage Rate for 48 dry mil thick membrane	3 gallons mixed liquids per 100 Square Feet
Gel Time Sprayed at 130°F. Tack Free Cure	Less than 2 minutes. Tack Free in 4 hours.

Note: The above values are not specifications. Open time, gel time and dry time will all vary depending on temperature and humidity at time of installation. It is recommended that on site testing be performed in job conditions prior to installation. The above values are controlled laboratory results. Results obtained in the field will differ under varying conditions.

Storage & Handling

Iron Sentry™ 121 Spray Polyurethane Sealer must be stored at temperatures between 50°F and 100°F. When transporting or storing material, be sure that the container is sealed and secure. Do not allow to freeze.

HEALTH & SAFETY INFORMATION: Health and safety information is available in the form of a Material Safety Data Sheet. This literature, describing proper precautions and personal protective equipment is available for review. To receive this information, please contact an MCPU Polymer Engineering representative. Before working with this product you must read and become familiar with this information.

IMPORTANT: The information contained in this technical data sheet is offered for your consideration, investigation, and verification. It is presented in good faith and is believed to be reliable. MCPU Polymer Engineering, however, makes no representation to either its accuracy or completeness. MCPU Polymer Engineering makes **NO WARRANTY**, express or implied, with respect to the data contained herein. The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of product evaluations) including any suggested recommendations are beyond our control. Therefore, **IT IS IMPERATIVE THAT YOU TEST OUR PRODUCTS**, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. **YOUR USE OF OUR PRODUCTS CONSTITUTES ACCEPTANCE.** This application-specific analysis must at least include testing to determine suitability from a technical, as well as health, safety, and environmental standpoint. All information and technical assistance is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and information. Any statement or recommendation to the contrary is unauthorized and shall not bind us.

For Additional Information, please contact:

Corporate Office:
708 S. Temescal, Suite 101
Corona, CA 92879
951-736-1881
www.mcpu.net

Manufacturing and R&D:
826 East Fourth St.
Pittsburg, KS 66762
620-231-4239



Updated 2-15-12